

CORIUM pul	
Roll Width	140 cm (+/-2%)
Roll Length (average)	30 m
Composition Surface	100% Polyurethane
Composition Base	50% Polyester + 30% Cotton + 20% Regenerated Leather
Weight Thickness	940 g/lm (+/-2%) 1,40 mm

Test	Method	Warp	Weft
Tensile Strength	DIN EN ISO 1421	1205 N/5 cm	917 N/5 cm
Tear Growth Resistance	DIN 53356 (Proc. A)	75 N	56 N
Seam Slippage Resistance	EN ISO 13936-2	≤ 4: passed	
Abrasion Test	EN ISO 12947-1, 2	> 100.000	
Permanent Creasing Ballyflex 23°C	DIN 53351	≥ 100.000 passed	≥ 100.000 passed
Bally Test - After Hydrolysis 14d 70° 95-98% rel. LF	DIN EN ISO 32100 (DIN 53351)	≥ 15.000 passed	≥ 15.000 passed
Fastness to Light	EN ISO 105-B02	5	
Fastness to Rubbing	EN ISO 105-X12	Dry: 5	Wet: 5
Flammability (cigarette)	EN 1021-1	Passed	
Odour	23°C; 40°C 24 hours VDA 270 C3 80°C	1 grade: passed 3 grade: passed	

Clean and Care Recommendations:

In case of stains, remove the dirt directly with a tissue and clean the stain with a neutral soap solution. Then clean with pure water.

